

Title	Teknipure C of C
Document Number	FM-8.2.5.3
Revision Date	November 15, 2023

Certificate of Conformance

Wiper Code:TC1PS2-99

LOT No: 527452-140524,527452-170524

Basis Weight (g/m ²) ASTM D3776			Thickness (mm) ASTM D1777-96			Orbital Shake Test for Particles IEST-RP-CC004.3 Section 6.1.4 (x10 ⁵ particle/m ²)				Fiber/Particles IEST-RP-CC004.3 Section 6.2.2 (particle/m ²)		Test For Sorbency Capacity & Rate IEST-RP-C004.3 Section 8.1					
Average	Lower SPEC Limit	Upper SPEC Limit	Thick- ness Average	Thick- ness Lower	Thick- ness Upper	>0.50 µm Average	>0.50 µm SPEC	>5.0 µm Average	>5.0 µm SPEC	>100 µm Average	>100 µm SPEC	Extrinsic Capacity (ml/m ²) Average	Extrinsic Capacity SPEC	Intrinsic Capacity (ml/g) Average	Intrinsic Capacity SPEC	Sorptive Rate (Sec.) Average	Sorptive Rate (Sec.) SPEC
120	115	124	0.46	0.42	0.48	8.6	< 10	1.4	< 2.0	446	< 600	423	> 400	2.7	> 2.3	< 1	< 1

Extractables - Short Term Extraction (g/m ²) IEST-RP-CC004.3 Section 7.1.2				Specific Extractable Ions (ug/g or ppm) IEST-RP-C004.3 Section 7.2.2.1B											
DI Water Average	DI Water SPEC	IPA Average	IPA SPEC	Sodium (Na ⁺) Average	Sodium (Na ⁺) SPEC	Potassium (K ⁺) Average	Potassium (K ⁺) SPEC	Calcium (Ca ²⁺) Average	Calcium (Ca ²⁺) SPEC	Chloride (Cl ⁻) Average	Chloride (Cl ⁻) SPEC	Magnesium (Mg ²⁺) Average	Magnesium (Mg ²⁺) SPEC		
0.009	<0.02	0.058	<0.080	0.21	<0.30	0.012	<0.20	0.23	<0.40	0.10	<0.20	0.22	<0.30		

Product Cleanliness Specifications

The raw materials used in the production of this finished product are compliant with IEST-RP-CC004.3 and in accordance with Teknipure specifications.

Product Packaging Specifications

The packaging materials, method & environment of this finished product are in accordance with Teknipure specifications.

Tested By: (Production Technician) _____ 张志豪

Inspected By: (Quality) _____ 王雪艳

Name (printed): _____ 王雪艳

Date of Manufacture: May.14/ May.17.2024

