

Title	Teknipure C of C
Document Number	FM-8.2.5.3
Revision Date	November 15, 2023

Certificate of Conformance

Wiper Code: TZ1MF-99

LOT No: 527490-050724

Basis Weight (g/m ²) ASTM D3776			Thickness (mm) ASTM D1777-96			Orbital Shake Test for Particles IEST-RP-CC004.3 Section 6.1.4 (x10 ⁶ particle/m ²)				Fiber/Particles IEST-RP-CC004.3 Section 6.2.2 (particle/m ²)		Test For Sorbency Capacity & Rate IEST-RP-C004.3 Section 8.1					
Average	Lower SPEC Limit	Upper SPEC Limit	Thick- ness Average	Thick- ness Lower	Thick- ness Upper	>0.50 µm Average	>0.50 µm SPEC	>5.0 µm Average	>5.0 µm SPEC	>100 µm Average	>100 µm SPEC	Extrinsic Capacity (ml/m ²) Average	Extrinsic Capacity SPEC	Intrinsic Capacity (ml/g) Average	Intrinsic Capacity SPEC	Sorptive Rate (Sec.) Average	Sorptive Rate (Sec.) SPEC
80	75	85	0.25	0.20	0.30	46.2	< 60.0	0.20	< 0.26	118	< 3500	339	>260	3.72	>3.5	< 1	< 1

Extractables - Short Term Extraction (g/m ²) IEST-RP-CC004.3 Section 7.1.2				Specific Extractable Ions (ug/g or ppm) IEST-RP-C004.3 Section 7.2.2.1B									
DI Water Average	DI Water SPEC	IPA Average	IPA SPEC	Sodium (Na ⁺) Average	Sodium (Na ⁺) SPEC	Potassium (K ⁺) Average	Potassium (K ⁺) SPEC	Calcium (Ca ²⁺) Average	Calcium (Ca ²⁺) SPEC	Chloride (Cl) Average	Chloride (Cl) SPEC	Magnesium (Mg ²⁺) Average	Magnesium (Mg ²⁺) SPEC
0.013	< 0.03	0.039	< 0.05	12.2	< 50.0	15.8	< 30.0	13.5	< 30.0	14.3	< 30.0	18.2	< 50

Product Cleanliness Specifications

The raw materials used in the production of this finished product are compliant with IEST-RP-CC004.3 and in accordance with Teknipure specifications.

Product Packaging Specifications

The packaging materials, method & environment of this finished product are in accordance with Teknipure specifications.

Tested By: (Production Technician) Bill
 Inspected By: (Quality) NAME
 Name (printed): Bill
 Date of Manufacture: Jul. 5, 2024



Toll Free: 844.309.2376



Quality@Teknipure.com



www.Teknipure.com