

Title	Teknipure C of C
Document Number	FM-8.2.5.3
Revision Date	November 15, 2023

Certificate of Conformance

Wiper Code: TZ1PCS1-44(150)

LOT No: 527438-280524

Basis Weight (g/m ²) ASTM D3776			Thickness (mm) ASTM D1777-96			Orbital Shake Test for Particles IEST-RP-CC004.3 Section 6.1.4 (x10 ⁶ particle/m ²)				Fiber/Particles IEST-RP-CC004.3 Section 6.2.2 (particle/m ²)		Test For Sorbency Capacity & Rate IEST-RP-C004.3 Section 8.1					
Average	Lower SPEC Limit	Upper SPEC Limit	Thick- ness Average	Thick- ness Lower	Thick- ness Upper	>0.50 µm Average	>0.50 µm SPEC	>5.0 µm Average	>5.0 µm SPEC	>100 µm Average	>100 µm SPEC	Extrinsic Capacity (ml/m ²) Average	Extrinsic Capacity SPEC	Intrinsic Capacity (ml/g) Average	Intrinsic Capacity SPEC	Sorptive Rate (Sec.) Average	Sorptive Rate (Sec.) SPEC
68	63	68	0.25	0.20	0.30	46.2	< 80.0	0.22	< 0.26	119	< 300	333	>280	4.7	> 4.0	< 1	< 1

Extractables - Short Term Extraction (g/m ²) IEST-RP-CC004.3 Section 7.1.2				Specific Extractable Ions (ug/g or ppm) IEST-RP-C004.3 Section 7.2.2.1B									
DI Water Average	DI Water SPEC	IPA Average	IPA SPEC	Sodium (Na ⁺) Average	Sodiu m (Na ⁺) SPEC	Potassiu m (K ⁺) Average	Potassium (K ⁺) SPEC	Calcium (Ca ²⁺) Average	Calcium (Ca ²⁺) SPEC	Chloride (Cl ⁻) Average	Chloride (Cl ⁻) SPEC	Magnesium (Mg ²⁺) Average	Magnesium (Mg ²⁺) SPEC
0.038	< 0.07	0.005	< 0.006	14.7	< 50.0	13.6	< 30.0	17.3	< 30.0	20.5	< 30.0	21.3	< 50.0

Product Cleanliness Specifications

The raw materials used in the production of this finished product are compliant with IEST-RP-CC004.3 and in accordance with Teknipure specifications.

Product Packaging Specifications

The packaging materials, method & environment of this finished product are in accordance with Teknipure specifications.

Tested By: (Production Technician) Bill
 Inspected By: (Quality) Monk
 Name (printed): Bill
 Date of Manufacture: May 28, 2024

