

Title	Teknipure C of C
Document Number	FM-8.2.5.1
Revision Date	June 24, 2023

Certificate of Conformance

Wiper Code: TC1PS1-20

LOT No: 527539

Basis Weight (g/m ²) ASTM D3776		Thickness (mm) ASTM D1777-96		Orbital Shake Test for Particles IEST-RP-CC004.3 Section 6.1.4 (x10 ⁶ particle/m ²)			Fiber/Particles IEST-RP-CC004.3 Section 6.2.2 (particle/m ²)		Test For Sorbency Capacity & Rate IEST-RP-C004.3 Section 8.1								
Average	Lower SPEC Limit	Upper SPEC Limit	Thickness Average	Thickness Lower	Thickness Upper	>0.50 μm Average	>0.50 μm SPEC	>5.0 μm Average	>5.0 μm SPEC	>100 μm Average	>100 μm SPEC	Extrinsic Capacity (ml/m ²) Average	Extrinsic Capacity SPEC	Intrinsic Capacity (ml/g) Average	Intrinsic Capacity SPEC	Sorbent Rate (Sec.) Average	Sorbent Rate (Sec.) SPEC
145	135	145	0.45	0.4	0.5	10.9	<15.0	0.75	<2.0	225	<600	418	>410	3.05	>2.8	<1	<1

Extractables - Short Term Extraction (g/m ²) IEST-RP-CC004.3 Section 7.1.2				Specific Extractable Ions (ug/g or ppm) IEST-RP-C004.3 Section 7.2.2.1B											
DI Water Average	DI Water SPEC	IPA Average	IPA SPEC	Sodium (Na ⁺) Average	Sodium (Na ⁺) SPEC	Potassium (K ⁺) Average	Potassium (K ⁺) SPEC	Calcium (Ca ²⁺) Average	Calcium (Ca ²⁺) SPEC	Chloride (Cl ⁻) Average	Chloride (Cl ⁻) SPEC	Magnesium (Mg ²⁺) Average	Magnesium (Mg ²⁺) SPEC		
0.017	<0.03	0.021	<0.08	0.13	<0.20	0.08	<0.10	0.13	<0.20	0.08	<0.10	0.08	<0.10		

Product Cleanliness Specifications

The raw materials used in the production of this finished product are compliant with IEST-RP-CC004.3 and in accordance with Teknipure specifications.

Product Packaging Specifications

The packaging materials, method & environment of this finished product are in accordance with Teknipure specifications.

<p>Tested By: (Production Technician) <i>Eric Hilkmann</i></p> <p>Inspected By: (Quality) <i>Eric Hilkmann</i></p>	<p>Name (printed): Eric Hilkmann</p> <p>Date of Manufacture: 11/01/2024</p>
--	---



Innovative Contamination Solutions



Toll Free: 844.309.2376



Quality@Teknipure.com



www.Teknipure.com