

Title	Teknipure C of A
Document Number	FM-8.2.5.3
Revision Date	February 12, 2024

Certificate of Analysis

Wiper Code: TZ1PCS1-11514

LOT No: 412504

Basis Weight (g/m ²) ASTM D3776			Thickness (mm) ASTM D1777-96			Orbital Shake Test for Particles IEST-RP-CC004.3 Section 6.1.4 (x10 ⁶ particle/m ²)				Fiber/Particles IEST-RP-CC004.3 Section 6.2.2 (x10 ² particle/m ²)		Test For Sorbency Capacity & Rate IEST-RP-C004.3 Section 8.1					
Average	Lower SPEC Limit	Upper SPEC Limit	Thick- ness Average	Thick- ness Lower	Thick- ness Upper	>0.50 µm Average	>0.50 µm SPEC	>5.0 µm Average	>5.0 µm SPEC	>100 µm Average	>100 µm SPEC	Extrinsic Capacity (ml/m ²) Average	Extrinsic Capacity SPEC	Intrinsic Capacity (ml/g) Average	Intrinsic Capacity SPEC	Sorptive Rate (Sec.) Average	Sorptive Rate (Sec.) SPEC
70	62	74	0.26	0.28	0.27	72	<80	0.21	<0.26	260	<300	350	>280	4.98	>4.0	0.38	<1

Extractables - Short Term Extraction (g/m ²) IEST-RP-CC004.3 Section 7.1.2				Specific Extractable Ions (ug/g or ppm) IEST-RP-C004.3 Section 7.2.2.1B									
DI Water Average	DI Water SPEC	IPA Average	IPA SPEC	Sodium (Na ⁺) Average	Sodium (Na ⁺) SPEC	Potassium (K ⁺) Average	Potassium (K ⁺) SPEC	Calcium (Ca ²⁺) Average	Calcium (Ca ²⁺) SPEC	Chloride (Cl ⁻) Average	Chloride (Cl ⁻) SPEC	Magnesium (Mg ²⁺) Average	Magnesium (Mg ²⁺) SPEC
0.036	<0.070	0.003	<0.006	44.5088	<50	10.4780	<30	12.4484	<30	24.9519	<30	2.3965	<50

Product Cleanliness Specifications

The raw materials used in the production of this finished product are compliant with IEST-RP-CC004.3 and in accordance with Teknipure specifications.

Product Packaging Specifications

The packaging materials, method & environment of this finished product are in accordance with Teknipure specifications.

Tested By: (Production Technician) Liang Jia En

Inspected By: (Quality) Chen Shi Quan

Name (printed): Xu Ying

Date of Manufacture: 10-09-2025

Expiration Date: 09-09-2028

